

PS 4/002

PS 4/002 is an unvulcanised centrifuged latex preserved with ultra low level of ammonia and other preservatives.

Types of Applications

PS 4/002 is suitable for all the normal latex compounding for the production of dipped/cast goods and adhesives, etc where ultra low level of ammonia is required.

| TYPICAL COLLOIDAL PROPERTIES | |
|--|-----------|
| Total Solid Content (%) | 61.5 min. |
| Ammonia Content (%) | 0.05 |
| Ford Cup 3, Viscosity @ 25 ⁰ C(sec) | 35.0 max. |
| VFA No. | 0.07 max. |
| Mechanical Stability (sec) | 750 min. |
| <i>(@ 55% TSC, dilution with DI water)</i> | |
| Coagulum, 80 mesh (ppm) | 100 max. |

Recommended Storage Conditions

It is important to store the product under shelter at temperature between 10⁰C and 38⁰C. Creaming of latex may still occurs during storage. Therefore it is necessary to mix well the latex before use. As the product is based on natural rubber latex, changes in colloidal properties may occur upon storage. It is recommended to test the colloidal properties of the latex if it is kept in storage over a long period of time.

HEAD OFFICE : 9/17 MOO 6, THEPKRASATTRI ROAD, RASADA, MUANG, PHUKET 83000, THAILAND
TEL : 076 211332, 076-211407 FAX : 076 215966 Tax ID: 0835558007926

FACTORY : 329 MOO 2, THUMYAI, THUNGSONG, NAKORN SRI THAMARAT 80110, THAILAND
TEL : 075 773123-4, FAX : 075 773122 www.mmguthrie.com.



บริษัท เอ็มเอ็มจี โพลีเมอร์ จำกัด

MMG POLYMER COMPANY LIMITED

Handling Precaution

Before handling any type of latices, read product information, Chemical Safety Data Sheets and container labels for safe use, physical and health hazard information.

Type of Packing

Available in both drum and bulk packing.

HEAD OFFICE : 9/17 MOO 6, THEPKRASATTRI ROAD, RASADA, MUANG, PHUKET 83000, THAILAND
TEL : 076 211332, 076-211407 FAX : 076 215966 Tax ID: 0835558007926

FACTORY : 329 MOO 2, THUMYAI, THUNGSONG, NAKORN SRI THAMARAT 80110, THAILAND
TEL : 075 773123-4, FAX : 075 773122 www.mmguthrie.com.

All information is given in good faith but without warranty. We will not accept liability for any damage, loss or patent infringement resulting from the use of this information.